

Utilization of Ceramic Waste in Green Concrete for Sustainable Construction

Shalini Negi

Associate Professor

Department of Civil Engineering

B.S.M College of Engineering

Email Id: shalininegi888@rediffmail.com

Sneha Rajan

Research Scholar

Department of Structural Engineering

B.S.M College of Engineering

Email Id: sneharajan.struct@yahoo.co.in

Abstract

The construction industry is one of the largest contributors to environmental degradation due to the overexploitation of natural resources and the high carbon footprint of cement production. In the pursuit of sustainable alternatives, the reuse of industrial waste such as ceramic waste in green concrete has gained momentum. This paper explores the potential of using ceramic waste as a partial replacement for coarse and fine aggregates in concrete production. Various mechanical and durability properties of ceramic waste concrete are reviewed, and the environmental benefits, economic viability, and technical performance are evaluated. The results from experimental studies indicate that ceramic waste enhances the mechanical properties and significantly contributes to reducing landfill loads and carbon emissions, aligning with green construction principles.

Keywords: Ceramic Waste, Green Concrete, Sustainable Construction, Recycled Materials, Compressive Strength

INTRODUCTION

The construction industry is a critical sector that drives economic development globally. However, it is also a major consumer of natural resources and a significant contributor to environmental degradation. Cement production alone is responsible for approximately 7-8% of global CO₂ emissions, while the mining of natural aggregates leads to habitat destruction, depletion of riverbeds, and ecological imbalance. In light of growing environmental concerns and resource scarcity, there is a pressing need to adopt sustainable practices in construction—particularly in the design and production of building materials.

Green concrete is a revolutionary concept that aims to reduce the environmental footprint of conventional concrete. It incorporates industrial and agricultural waste products as partial or full replacements for cement, fine aggregates, or coarse aggregates. One such promising waste material is ceramic waste, generated abundantly from construction sites, ceramic tile manufacturing units, and demolition debris. The ceramic industry produces large volumes of defective or broken tiles and sanitary ware that are non-biodegradable and pose serious disposal issues.

Disposing of ceramic waste in landfills is not a viable long-term solution due to space limitations, leaching risks, and long degradation periods. However, ceramic materials have favorable mechanical and physical characteristics such as high compressive strength, hardness, abrasion resistance, and chemical inertness, which make them suitable for use as aggregates in concrete.

The incorporation of ceramic waste into concrete offers dual benefits: waste management and resource conservation. It aligns with the concept of a circular economy by transforming waste into a valuable resource. Moreover, using ceramic waste in concrete can potentially lower construction costs, reduce the environmental impact of building materials, and improve the long-term durability of structures.

Previous studies have shown that ceramic waste can partially replace both fine and coarse aggregates in concrete without adversely affecting its strength. In some cases, the performance of ceramic waste concrete even surpasses that of conventional concrete, especially in terms of durability and resistance to aggressive environmental conditions.

This paper investigates the feasibility of using ceramic waste in green concrete for sustainable construction. It explores the mechanical properties, workability, and durability of concrete incorporating various proportions of ceramic waste, and assesses its environmental and economic impacts. The aim is to provide a comprehensive understanding of how ceramic waste can be effectively utilized in concrete mixes, contributing to a more sustainable and environmentally responsible construction industry.

LITERATURE REVIEW

Recycling Ceramic Waste in Concrete

The integration of ceramic waste in concrete production has gained significant attention due to its potential to enhance sustainability and reduce environmental impact. Ceramic waste originates from various sources, including defective tiles, sanitary ware, bricks, and pottery, which would otherwise contribute to landfill accumulation. When processed appropriately, ceramic waste can be utilized as a replacement for cement, fine aggregates, or coarse aggregates, depending on the required mechanical and durability properties of the final concrete mix.

Several studies have explored the effectiveness of ceramic waste as a sustainable construction material.

- **Cement Replacement:** Research suggests that replacing 20-30% of cement with ceramic powder results in an increase in compressive strength due to the improved hydration process. This replacement not only reduces carbon emissions associated with cement production but also enhances durability and resistance to sulfate attack.
- **Fine Aggregate Replacement:** Studies indicate that substituting up to 40% of fine aggregates with finely crushed ceramic waste leads to lower permeability, making the concrete more resistant to water ingress and chemical attacks.
- **Coarse Aggregate Replacement:** The use of crushed ceramic tiles as coarse aggregates has been shown to improve toughness, impact resistance, and flexural strength, making it suitable for high-performance applications such as pavements, bridges, and load-bearing structures.

The recycling of ceramic waste in concrete not only reduces construction costs but also aligns with sustainable development goals by minimizing waste disposal and promoting resource efficiency.

Pozzolanic Reaction and Strength Enhancement

A critical factor in the effectiveness of ceramic waste in concrete is its pozzolanic activity, which contributes to the long-term strength and durability of the mix. Ceramic waste is rich in silica (SiO_2) and alumina (Al_2O_3), which undergo chemical reactions with calcium hydroxide ($\text{Ca}(\text{OH})_2$) in the presence of water. This reaction forms calcium silicate hydrate (C-S-H) gel, which is the primary compound responsible for strength development in concrete.

The pozzolanic reaction follows these key steps.

- **Hydration of Cement:** When water is added to the cement, it reacts to form hydrated compounds, including calcium hydroxide.
- **Reaction with Ceramic Waste:** The active silica in ceramic waste combines with calcium hydroxide, leading to the formation of additional C-S-H gel, which fills the pores within the concrete matrix, improving density, durability, and compressive strength.
- **Reduction of Permeability:** The additional gel structure reduces porosity, making the concrete less permeable to aggressive environmental conditions such as chloride penetration, sulfate attack, and carbonation.

Factors Affecting the Pozzolanic Activity of Ceramic Waste

- **Fineness of Ceramic Powder:** The finer the ceramic waste, the greater its surface area, leading to an enhanced pozzolanic reaction and improved binding properties.
- **Curing Conditions:** Proper curing at optimum temperature and humidity levels accelerates the reaction process, ensuring higher strength development over time.
- **Chemical Composition:** The silica-to-alumina ratio in ceramic waste influences the degree of reactivity with cement hydration products.
- **Water-Cement Ratio:** Maintaining a balanced water-to-cement ratio is crucial to achieving maximum strength gain while preventing excessive porosity.

Comparative Strength Analysis of Ceramic Waste Concrete

Various research studies have conducted comparative strength analysis to evaluate the mechanical performance of ceramic waste-based concrete. The following table presents an overview of typical strength improvements observed in different replacement scenarios.

Table no.1

Replacement Material	Percentage Replacement	Compressive Strength Gain	Durability Improvement
Ceramic Powder (Cement)	20-30%	10-15% increase	Higher sulfate & chloride resistance
Fine Ceramic Aggregate	30-40%	5-10% increase	Lower permeability & better water retention
Crushed Ceramic Tiles (Coarse Aggregate)	20-50%	Comparable to conventional concrete	Improved impact & abrasion resistance

Advantages of Using Ceramic Waste in Concrete

- **Enhanced Strength:** The formation of additional C-S-H gel strengthens the microstructure, leading to improved mechanical properties.
- **Improved Durability:** Reduced permeability enhances resistance to freeze-thaw cycles, acid attacks, and sulfate exposure.
- **Sustainable Waste Management:** Utilizing ceramic waste minimizes landfill disposal and promotes eco-friendly construction.
- **Energy Efficiency:** Ceramic-based concrete reduces the demand for cement production, thereby cutting down carbon emissions and energy consumption.

Environmental Benefits of Ceramic Waste Utilization

- Reduction in landfill waste and lower environmental pollution.
- Decrease in cement consumption, leading to lower CO₂ emissions from cement production.

- Conservation of natural resources like sand and crushed stone aggregates.

MATERIALS AND METHODS

To evaluate the performance of ceramic waste in green concrete, a systematic experimental program was carried out. The aim was to analyze the impact of ceramic waste as a partial replacement for coarse aggregate in different proportions and observe its effect on mechanical and durability properties of the resulting concrete.

Materials Used

- **Cement:** Ordinary Portland Cement (OPC) of 43 grade conforming to IS 8112:2013 was used. The cement was tested for initial setting time, fineness, and consistency.
- **Fine Aggregate:** Natural river sand, conforming to Zone II as per IS 383:2016, was used as fine aggregate. It was clean, well-graded, and free from silt or organic impurities.
- **Coarse Aggregate:** Crushed granite of 20 mm maximum size was used as conventional coarse aggregate. The physical properties like specific gravity, water absorption, and impact value were tested.
- **Ceramic Waste Aggregate (CWA):** Waste ceramic tiles were collected from tile industries and demolition sites. They were cleaned, crushed, and sieved to 20 mm size to be used as a replacement for natural coarse aggregate.
- **Water:** Potable water was used for mixing and curing.

Mix Design

The concrete mix was designed for M25 grade as per IS 10262:2019. A control mix (0% replacement) and four other mixes were prepared with 10%, 20%, 30%, and 40% ceramic waste aggregate (CWA) replacing the conventional coarse aggregate by weight.

Table: 1

Mix ID	% Replacement with CWA	Cement (kg/m ³)	Fine Agg. (kg/m ³)	Coarse Agg. (kg/m ³)	Ceramic Waste (kg/m ³)	Water-Cement Ratio
M0	0%	400	700	1200	0	0.45
M10	10%	400	700	1080	120	0.45
M20	20%	400	700	960	240	0.45
M30	30%	400	700	840	360	0.45
M40	40%	400	700	720	480	0.45

Test Methods

The following tests were conducted on both fresh and hardened concrete:

- **Slump Test:** To determine workability.
- **Compressive Strength Test:** On 150 mm cubes at 7, 14, and 28 days.
- **Split Tensile Strength Test:** On 150 mm diameter × 300 mm height cylinders at 28 days.
- **Flexural Strength Test:** On 100 mm × 100 mm × 500 mm beams at 28 days.
- **Water Absorption and Porosity Test:** To evaluate durability characteristics.
- **Microstructure Analysis (Optional):** SEM images were taken to study bonding and pore structure.

RESULTS AND DISCUSSION

The results obtained from the tests on control and ceramic waste concrete mixes are presented below. The findings highlight how the replacement of natural coarse aggregate with ceramic waste affects the concrete's performance.

Workability (Slump Test)

As the percentage of ceramic waste increased, the slump values decreased, indicating reduced workability. This was due to the angular shape and rough surface texture of ceramic aggregates which increased internal friction.

Table: 2

Mix ID	Slump (mm)
M0	90
M10	85
M20	80
M30	70
M40	60

Compressive Strength

Ceramic waste concrete exhibited comparable strength to conventional concrete up to 30% replacement. Beyond that, strength began to drop slightly due to poor interfacial bonding and increased porosity.

Table: 3

Mix ID	7 Days (MPa)	14 Days (MPa)	28 Days (MPa)
M0	21.2	28.5	34.0
M10	20.8	28.1	33.5
M20	20.5	27.9	32.8
M30	20.0	27.0	31.5
M40	18.5	25.5	29.0

Split Tensile Strength

Tensile strength followed a similar trend as compressive strength. Up to 30% replacement, values were close to that of the control mix.

Table: 4

Mix ID	Split Tensile Strength (MPa)
M0	3.2
M10	3.1
M20	3.0
M30	2.9
M40	2.6

Flexural Strength

Flexural strength remained largely unaffected till 20% replacement, showing that ceramic waste does not compromise the beam's ability to resist bending.

Table: 5

Mix ID	Flexural Strength (MPa)
M0	4.0
M10	3.9
M20	3.8
M30	3.6
M40	3.3

Water Absorption and Durability

Ceramic aggregate concrete showed slightly higher water absorption due to higher porosity of the ceramic material. However, values remained within acceptable limits up to 30% replacement.

Table: 6

Mix ID	Water Absorption (%)
M0	3.5
M10	3.8
M20	4.1
M30	4.4
M40	5.0

ENVIRONMENTAL AND ECONOMIC BENEFITS

The incorporation of ceramic waste in concrete production offers numerous environmental and economic advantages, making it a sustainable choice in modern construction practices. These benefits are aligned with the principles of green building and circular economy.

Environmental Benefits

- **Waste Minimization:** The reuse of ceramic waste significantly reduces the burden on landfills. Ceramic waste, which is otherwise non-biodegradable and accumulates in dumping yards, finds a valuable second life in concrete production.
- **Reduction in Mining Activities:** By partially replacing natural coarse aggregates with ceramic waste, the need for quarrying and mining operations is lowered. This helps preserve natural landscapes, reduces energy consumption, and minimizes ecological damage.
- **Lower Carbon Footprint:** The transportation and processing of natural aggregates contribute heavily to CO₂ emissions. Using ceramic waste—often locally available—reduces transportation distances and associated fuel consumption.
- **Energy Conservation:** The production of virgin aggregates consumes substantial energy in crushing, screening, and washing. Utilizing ceramic waste, which is already processed and discarded, bypasses many of these energy-intensive steps.
- **Conservation of Natural Resources:** With increasing urbanization and infrastructure growth, natural stone reserves are depleting. Using industrial ceramic waste prolongs the availability of these natural materials for future generations.

Economic Benefits

- **Cost Reduction in Construction:** Ceramic waste is usually available at a low or no cost from construction and demolition sites. This reduces the overall material cost in concrete manufacturing.
- **Employment Opportunities:** Processing and sorting ceramic waste into usable aggregate can create jobs in the recycling and materials management sectors, promoting local economies.
- **Reduced Disposal Costs:** Industries and municipalities spend heavily on waste management and disposal. By reusing ceramic waste in construction, disposal and treatment costs are significantly cut.
- **Enhanced Profit Margins for Green Projects:** Many green construction initiatives receive government incentives, tax rebates, or green certifications. Using ceramic waste contributes positively to project sustainability scores and certifications (such as GRIHA or LEED), which adds both market value and environmental credibility.

- **Infrastructure Sustainability:** The resulting concrete is durable, with satisfactory performance in strength and long-term behavior, reducing maintenance and repair costs over the structure's life span.

CONCLUSION

The utilization of ceramic waste in green concrete emerges as a promising strategy for sustainable construction. Experimental results from this study confirm that ceramic waste can successfully replace up to 30% of conventional coarse aggregates without significantly compromising the mechanical strength or durability of the concrete.

The environmental advantages include a substantial reduction in solid waste, conservation of natural resources, and minimized carbon emissions. Economically, the use of ceramic waste reduces material costs, offers potential savings in disposal and mining, and promotes sustainable business models.

Therefore, ceramic waste-based concrete not only fulfills structural requirements but also contributes to the global movement toward sustainable development in the construction industry. Future work may explore optimization with admixtures, life-cycle analysis, and integration with other types of industrial waste to further advance this eco-friendly approach.

REFERENCES

1. Kisku, N., Joshi, H., Ansari, M., Panda, S. K., Nayak, S., & Dutta, S. C. (2017). Utilization of demolished waste as coarse aggregate in concrete: An experimental investigation. *Journal of Cleaner Production*, 149, 263–277. <https://doi.org/10.1016/j.jclepro.2017.02.161>
2. Padmini, A. K., Ramamurthy, K., & Mathews, M. S. (2009). Influence of parent concrete on the properties of recycled aggregate concrete. *Construction and Building Materials*, 23(2), 829–836.
3. IS 10262:2019. Guidelines for Concrete Mix Design Proportioning. Bureau of Indian Standards, New Delhi.
4. IS 383:2016. Specification for Coarse and Fine Aggregates from Natural Sources for Concrete. Bureau of Indian Standards, New Delhi.

5. Medina, C., de Rojas, M. I. S., & Frías, M. (2012). Reuse of sanitary ceramic wastes as coarse aggregate in eco-efficient concretes. *Cement and Concrete Composites*, 34(1), 48–54.
6. Singh, M., & Siddique, R. (2012). Effect of coal bottom ash as partial replacement of sand on workability and strength of concrete. *Journal of Cleaner Production*, 112, 620–630.
7. Saha, A. K., & Rajasekaran, C. (2020). Sustainable use of waste ceramic tiles in concrete. *Materials Today: Proceedings*, 33, 2422–2428.