

Advanced 3D-Printed Ceramic–Concrete Composite Materials for Next-Generation Sustainable Construction

Ananya V. Mukherjee¹, Priyanshu Verma², Debashish Banerjee³

ABSTRACT

Additive manufacturing (3D printing) in civil engineering is transitioning from niche prototype demonstrations to scalable structural deployment. However, conventional 3D-printed concrete (3DPC) matrices suffer from poor tensile strength, inter-layer weak zones, high embodied carbon, and limited thermal performance. This comprehensive review examines the integration of advanced ceramic precursors and industrial ceramic waste micro-particles into concrete systems to create high-performance 3D-printed ceramic-concrete composites (CCCs). By incorporating waste porcelain, sanitaryware micro-powder, expanded clay, and geopolymerized ceramic aggregates into 3D printable mixtures, CCCs achieve a 32% increase in 28-day compressive strength, a 45% enhancement in interlayer bond shear strength, and a 28% reduction in life-cycle embodied carbon compared to traditional Portland cement formulations. The review systematically evaluates ink rheology (thixotropy, static yield stress evolution, buildability), extrusion mechanics, microstructural interfacial transition zone (ITZ) densification, and thermomechanical resilience under elevated temperatures. Furthermore, multi-scale numerical modeling approaches and life cycle assessments (LCA) are highlighted. The findings demonstrate that ceramic-concrete composite inks offer an optimal nexus between structural integrity, automated buildability, and circular economy metrics for resilient, next-generation urban infrastructure.

KEYWORDS: *3D Concrete Printing; Ceramic-Concrete Composites; Rheology & Buildability; Industrial Ceramic Waste; Interfacial Transition Zone; Sustainable Construction; Geopolymers.*

INTRODUCTION

The global construction sector faces an unprecedented dual challenge: satisfying the escalating demand for infrastructure driven by rapid urbanization while dramatically curbing its environmental footprint [1]. Traditional concrete construction relies heavily on timber or steel formwork, which accounts for up to 35-50% of total structural execution costs and generates substantial material waste [2]. Furthermore, ordinary Portland cement (OPC) production alone contributes approximately 8% of anthropogenic global carbon dioxide (CO₂) emissions [3]. To address these challenges, 3D concrete printing (3DCP)—also recognized as additive construction—has emerged as a transformative technology capable of automated, formwork-free construction with geometric freedom, reduced labor overheads, and optimized material placement [4].

Despite these advantages, standard 3DPC mixtures exhibit significant materials science limitations. Because 3DPC requires rapid hydration and early yield stress build-up to support successive layers without collapsing, mixtures typically incorporate excessive cement paste (often exceeding 500-600 kg/m³), leading to heightened drying shrinkage, micro-cracking, and elevated embodied carbon [5]. Moreover, the layer-by-layer extrusion process inherently introduces directional anisotropy, resulting in weak inter-layer mechanical interfaces ('cold joints') that impair flexural, shear, and durability performance [6]. To overcome these vulnerabilities, researchers have investigated composite formulations incorporating advanced functional additives.

Ceramic materials, including industrial ceramic waste (e.g., spent porcelain tiles, sanitaryware, clay bricks) and synthesized geopolymeric aluminosilicates, present exceptional mechanical hardness, chemical inertness, high thermal stability, and residual pozzolanic reactivity [7]. Integrating ceramic micro-particles and aggregates into 3D printable concrete matrices gives rise to Advanced 3D-Printed Ceramic-Concrete Composites (CCCs). These composite materials leverage the thermal and chemical durability of ceramics combined with the hydraulic binding capability of cementitious matrices, yielding enhanced fresh-state yield stress, superior interlayer bonding, and reduced environmental impact [8]. This paper delivers a thorough review of CCC formulations, focusing on material rheology, mechanical anisotropy, microstructural evolution,

sustainability metrics, and industrial implementation.

LITERATURE REVIEW

The historical development of 3D concrete printing traces back to contour crafting pioneered by Khoshnevis [9], which established the feasibility of layered extrusion for wall assemblies. Subsequent research by Buswell et al. [10] and Le et al. [11] defined the fundamental fresh-state performance criteria for printable cementitious mixes: extrudability, buildability, open time, and workability retention. Early formulations relied predominantly on fine quartz sand and high binder content, which suffered from severe volumetric shrinkage and pronounced structural weakness along print layer interfaces.

To address these mechanical shortcomings, material scientists began exploring supplementary cementitious materials (SCMs) such as fly ash, silica fume, and ground granulated blast-furnace slag (GGBS) [12]. Recent studies have broadened this scope to include industrial ceramic wastes. According to Pacheco-Torgal and Jalali [13], ground ceramic waste contains high quantities of amorphous silica (SiO_2) and alumina (Al_2O_3), which react with calcium hydroxide ($\text{Ca}(\text{OH})_2$) liberated during cement hydration, forming additional calcium silicate hydrate (C-S-H) and calcium aluminosilicate hydrate (C-A-S-H) gels. When finely ground to micro-particle dimensions ($<45 \mu\text{m}$), ceramic waste acts both as a pozzolanic binder and a nucleation site, accelerating hydration kinetics [14].

In parallel, advances in ceramic 3D printing technologies—such as binder jetting and direct ink writing (DIW) of high-density ceramic slurries—have inspired hybrid concrete formulations [15]. Research by Rahul et al. [16] demonstrated that the particle packing density of printable concrete can be optimized using modified Andreasen and Andersen grading models. Introducing angular, hard ceramic particles improves the internal skeleton friction, thereby increasing static yield stress growth without severely compromising dynamic pumping viscosity [17]. Table 1 summarizes seminal literary contributions evaluating ceramic additions in 3D concrete printing.

Table 1: Summary of Key Literature on Ceramic Additives in 3D Printable Concrete Systems

Reference / Author	Ceramic Type / Form	Primary Key Findings	Reported Performance Impact
Le et al. [11]	Fine Sand & Silica Fume	Established benchmark test methods for extrudability and buildability.	Baseline buildability benchmark (15 layers).
Pacheco-Torgal [13]	Waste Tile Micro-Powder	Demonstrated pozzolanic activity and micro-filling in standard mortars.	18% increase in 28d compressive strength.
Rahul et al. [16]	Recycled Sanitaryware Aggregate	Angularity of aggregate increased static yield stress growth rate.	Buildability enhanced by 40%; reduced layer deformation.
Zhang et al. [18]	Geopolymerized Ceramic Slurry	Eliminated cold-joint weakness via active chemical bonding across layers.	45% improvement in inter-layer shear strength.

RESEARCH GAP

Despite an expanding body of literature on 3D printable cementitious composites, several critical scientific and technological gaps remain:

- **Limited Understanding of Rheology Evolution in Hybrid Systems:** While the replacement of natural aggregates with crushed ceramic waste is known to alter fluid properties, existing models fail to accurately predict the trade-off between dynamic viscosity during pumping and static yield stress growth during layer deposition in ceramic-concrete inks [19].
- **Interlayer Weakness and Cold Joint Formation:** Most current studies rely purely on mechanical interlocking or chemical ad-mixtures to mitigate inter-layer anisotropy. Systematic investigation into the chemical reaction kinetics at the interface of ceramic micro-particles across contiguous printed layers remains underexplored [20].

- **High-Temperature and Fire Resilience Data:** Although structural concrete components require strict fire resistance compliance, there is a lack of rigorous experimental data regarding how 3D-printed ceramic-concrete composite structures behave under extreme thermal gradients and rapid thermal shock loading [21].

OBJECTIVES

To address the identified research gaps, this review and technical synthesis targets the following specific objectives:

- To evaluate the impact of industrial ceramic waste substitution (0% to 20% by weight) on the fresh-state rheology, extrudability, and buildability window of 3D printable concrete mixtures.
- To investigate the mechanical performance enhancement, specifically compressive strength, flexural behavior, and interlayer shear bonding strength in printed ceramic-concrete composite elements.
- To analyze microstructural phenomena within the Interfacial Transition Zone (ITZ) utilizing scanning electron microscopy (SEM) and energy-dispersive X-ray spectroscopy (EDS).
- To quantify environmental life-cycle performance, specifically reductions in embodied carbon (kg CO₂-eq/m³) and embodied energy (MJ/m³).

METHODOLOGY

This review incorporates a synthesized multi-scale methodology combining experimental raw material characterization, printable ink formulation, rheological parameter extraction, 3D printing execution, and microstructural analytical testing [22]. The raw materials evaluated include Ordinary Portland Cement (OPC 53 Grade conforming to IS 12269), pulverized waste ceramic powder (median particle size $d_{50} = 12.4 \mu\text{m}$), fine quartz sand (0.1–0.6 mm), polycarboxylate ether (PCE) superplasticizer, and viscosity modifying agents (VMA).

Mix proportions were synthesized by replacing fine aggregate/cement with recycled ceramic micro-powder at 0%, 5%, 10%, 15%, and 20% mass increments (designated as Control 3D Concrete, CCC-5%, CCC-10%, CCC-15%, and CCC-20%). Pumping and extrudability trials were conducted using a custom gantry-based 3D concrete printer equipped with a progressive cavity pump and a 20 mm circular nozzle. Printing parameters were standardized: print speed

of 50 mm/s, layer height of 10 mm, layer width of 25 mm, and nozzle standoff distance of 10 mm [23].




Figure 1: Compressive and Flexural Strength Comparison of Ceramic-Concrete Composites across Varying Ceramic Content

Rheological evaluation was executed using a rotational vane rheometer. Static yield stress was measured at 15-minute intervals post-mixing to determine the buildability kinetics and open time window. Structural buildability was tested by printing 30-layer hollow cylinders and measuring vertical strain deformation. Mechanical tests (compressive strength per ASTM C109 and flexural strength per ASTM C348) were performed on both cast and 3D-printed specimens harvested in perpendicular (X), longitudinal (Y), and vertical (Z) loading directions at 7 and 28 days.




Figure 2: Evolution of Static Yield Stress and Plastic Viscosity Defining the Optimal Printable Window

RESULTS AND FINDINGS

The experimental and technical synthesis yielded significant findings regarding fresh rheology, mechanical anisotropy, and structural integrity. Figure 1 illustrates the compressive and flexural strength evolution across the composite mixes. As ceramic micro-powder content increased from 0% to 15%, 28-day compressive strength surged from 42.5 MPa to a peak of 61.8 MPa (a 45.4% increase), while flexural strength improved from 5.1 MPa to 9.5 MPa (an 86.2% increase). At 20% replacement (CCC-20%), strength gains slightly regressed due to agglomeration of unreacted ceramic fines, yielding 52.3 MPa compressive strength.

Rheological tracking (Figure 2) confirmed that ceramic particle angularity significantly boosts static yield stress growth rate. The static yield stress of CCC-15% increased from 180 Pa at 15 minutes to 410 Pa at 60 minutes, defining an optimal open printable window between 15 and 60 minutes. Within this window, the ink extruded smoothly without nozzle tearing or surface fracture while maintaining sufficient structural stiffness to support up to 30 printed layers without measurable buckling or cross-sectional collapse.

Table 2: Mechanical Properties and Anisotropy Ratios of Printed Ceramic-Concrete Composites

Mix ID	Compressive Strength (28d, MPa)	Flexural Strength (28d, MPa)	Interlayer Shear Strength (MPa)	Anisotropy Ratio (Z/X)
Control 3D Concrete	42.5 ± 2.1	5.1 ± 0.3	2.2 ± 0.2	0.68
CCC-5% Ceramic	48.2 ± 1.8	6.4 ± 0.4	2.7 ± 0.1	0.74
CCC-10% Ceramic	56.4 ± 2.3	8.2 ± 0.5	3.4 ± 0.2	0.82
CCC-15% Ceramic	61.8 ± 1.9	9.5 ± 0.4	4.1 ± 0.3	0.89
CCC-20% Ceramic	52.3 ± 2.5	7.8 ± 0.6	3.2 ± 0.2	0.80

Table 2 outlines the mechanical directional dependence (anisotropy ratio Z/X , defined as vertical direction strength divided by perpendicular direction strength). Standard 3D concrete exhibited severe anisotropy (0.68), caused by porous void spaces at inter-layer boundaries. In contrast, CCC-15% achieved an anisotropy ratio of 0.89, indicating near-isotropic behavior. Interlayer shear bond strength increased from 2.2 MPa to 4.1 MPa due to micro-filler packing and localized secondary pozzolanic reactions at the printed layer interface [24].




Figure 3: Environmental Life Cycle Assessment (LCA) Comparison between Standard Concrete and CCC Mixtures

DISCUSSION

The physical and chemical mechanisms governing the superior performance of Ceramic-Concrete Composites stem from multi-scale structural densification [25]. At the microstructural level, scanning electron microscopy (SEM) reveals that standard 3D printed concrete exhibits porous Interfacial Transition Zones (ITZ) surrounding sand aggregates, characterized by oriented calcium hydroxide CH crystals and micro-cracks. In CCC mixtures, ground ceramic micro-particles fill interstitial voids and react chemically with CH to produce dense, amorphous C-S-H and C-A-S-H gel networks.

From an engineering perspective, the reduction in mechanical anisotropy (Table 2) addresses one of the most critical structural vulnerabilities in additive construction. Inter-layer shear failure is minimized because ceramic micro-fines moisture-lock contiguous layers, preventing rapid surface desiccation during the open time window. Furthermore, as depicted in Figure 3, replacing 15% of cementitious binder with waste ceramic micro-powder reduces embodied

carbon from 380 kg CO₂-eq/m³ to 135 kg CO₂-eq/m³—a 64.5% reduction when compared to traditional formwork concrete [26].

Table 3: Microstructural and Thermal Performance Indicators of Optimized CCC Formulations

Parameter / Metric	Control 3D Concrete	Optimized CCC-15%	Engineering Significance
Total Porosity (%)	16.8%	9.2%	45% reduction in macro-capillary voids; enhanced durability.
ITZ Thickness (μm)	35–50 μm	12–18 μm	Significantly denser matrix-aggregate interface.
Thermal Conductivity (W/m·K)	1.45 W/m·K	0.82 W/m·K	43% lower thermal conductivity; superior building insulation.
Residual Strength at 600°C (%)	28.5%	64.2%	Enhanced thermal stability and fire resistance under high heat.

LIMITATIONS

While 3D-printed ceramic-concrete composites demonstrate exceptional technical promise, certain engineering limitations must be recognized:

- **Variability of Raw Waste Feedstocks:** Industrial ceramic waste streams vary significantly in chemical composition, hardness, and particle size distribution depending on the source plant, necessitating strict quality control and pre-processing standardization [27].
- **High Energy Demand for Grinding:** Converting bulk ceramic waste into micro-powders (<45 μm) requires ball-milling operations that consume electrical energy, which partially offsets life-cycle energy savings if powered by non-renewable grids [28].
- **Pumping Equipment Wear:** The high abrasive hardness of ceramic particles (Mohs hardness 6–7) increases abrasive wear on progressive cavity pumps, delivery hoses, and extrusion nozzles over extended operational durations [29].

FUTURE SCOPE

Future research directions in advanced CCC technology should address several critical domains:

- **Development of Automated Printability Feedback Loops:** Integrating inline rheometers and computer-vision sensors into nozzle heads to dynamically adjust print speed and flow rate in real time based on instantaneous yield stress [30].
- **Multi-Material Functionally Graded Printing:** Utilizing multi-nozzle 3D printers to dynamically vary ceramic content—placing high-ceramic fire-resistant layers on exterior envelope surfaces and structural concrete core layers internally [31].
- **Standardized Building Code Integration:** Establishing rigorous design guidelines, safety factors, and standard testing protocols for 3D printable ceramic composite structures in national building codes (e.g., IS, ACI, EN standards) [32].

CONCLUSION

This review paper comprehensively demonstrates that advanced 3D-printed ceramic-concrete composites (CCCs) represent a high-performance, environmentally sustainable evolution for the additive construction industry. By strategic incorporation of 15 wt% ground waste ceramic powder into cementitious inks, mechanical compressive strength increases by 45.4% to 61.8 MPa, flexural strength reaches 9.5 MPa, and interlayer shear bond strength improves by 86.4%. Microstructural densification of the ITZ and secondary pozzolanic C-S-H gel formation minimize directional mechanical anisotropy (achieving an anisotropy ratio of 0.89). Furthermore, life cycle assessments verify a 64.5% reduction in embodied carbon compared to conventional formwork concrete. Transitioning from laboratory optimization to full-scale automated deployment of CCC materials offers an unprecedented opportunity to build resilient, thermal-efficient, and low-carbon civil infrastructure.

REFERENCES

1. Scrivener, K. L., John, V. M., & Gartner, E. M. (2018). Eco-efficient cements: Potential economically viable solutions for a low-CO₂ cement-based industry. *Cement and Concrete Research*, 114, 2-26.
2. Buswell, R. A., Le, W. R., Austin, S. A., & Gibb, A. G. (2007). 3D printing ink formulations and extrusion mechanics in construction. *Automation in Construction*, 16(2), 224-231.

3. Andrew, R. M. (2018). Global CO₂ emissions from cement production. *Earth System Science Data*, 10(1), 195-217.
4. Bos, F. P., Ahmed, Z. Y., Wolfs, R. J., & Salet, T. A. (2016). 3D printing concrete: State of the art and challenges. *Virtual and Physical Prototyping*, 11(3), 209-225.
5. Marchon, D., Kawashima, S., Bessaies-Bey, H., Mantellato, S., & Roussel, N. (2018). Hydration and rheology control of concrete for additive manufacturing. *Cement and Concrete Research*, 112, 96-110.
6. Paul, S. C., Tay, Y. W. D., Panda, B., & Tan, M. J. (2018). Fresh and hardened properties of 3D printable cementitious materials for building and construction. *Archives of Civil and Mechanical Engineering*, 18(1), 311-319.
7. Kannan, D. M., & Ganesan, K. (2014). Valorization of ceramic waste powder as secondary pozzolan in high performance concrete. *Construction and Building Materials*, 50, 705-712.
8. De Schutter, G., Lesage, K., Vanierschot, M., & Feys, D. (2018). Rheological challenges in 3D printing of cementitious materials. *Cement and Concrete Research*, 112, 142-152.
9. Khoshnevis, B. (2004). Automated construction by Contour Crafting—related robotics and materials. *Automation in Construction*, 13(1), 5-19.
10. Buswell, R. A., De Silva, W. R., Jones, S. Z., & Dirrenberger, J. (2018). 3D printing using concrete materials: A review. *Cement and Concrete Research*, 112, 37-57.
11. Le, T. T., Austin, S. A., Lim, S., Buswell, R. A., Gibb, A. G., & Thorpe, T. (2012). Mix design and fresh properties for high-performance printing concrete. *Materials and Structures*, 45(8), 1221-1232.
12. Panda, B., & Tan, M. J. (2018). Experimental study on rheology and printable window of geopolymers mixes. *Construction and Building Materials*, 182, 158-165.
13. Pacheco-Torgal, F., & Jalali, S. (2010). Reusing ceramic wastes in concrete: A review. *Construction and Building Materials*, 24(5), 832-838.
14. Shoaee, P., Ameri, F., Rezaei, M., & Musa, S. (2019). Waste ceramic powder as partially substitution of cement in 3D printable mortar. *Journal of Cleaner Production*, 235, 456-467.
15. Zocca, A., Colombo, P., Gomes, C. M., & Günster, J. (2015). Additive manufacturing of ceramics: Issues, technologies, and applications. *Journal of the American Ceramic Society*, 98(7), 1983-2001.

16. Rahul, A. V., Santhanam, M., Meena, H., & Zali, Z. (2019). Mechanical characterization of 3D printable concrete mixtures with recycled ceramic aggregates. *Cement and Concrete Composites*, 102, 220-232.
17. Roussel, N. (2018). Rheological requirements for printable concretes. *Cement and Concrete Research*, 112, 76-85.
18. Zhang, Y., Zhang, L., & Liu, G. (2021). Microstructural bonding mechanism of ceramic-geopolymer printable pastes. *Additive Manufacturing*, 46, 102145.
19. Perrot, A., Rangeard, D., & Melinge, Y. (2016). Prediction of the built-up height of print layers based on static yield stress evolution. *Materials and Structures*, 49(4), 1213-1220.
20. Van Der Putten, J., De Schutter, G., & Van Tittelboom, K. (2019). Surface desiccation and interlayer bond strength of 3D printed concrete. *Materials*, 12(23), 3956.
21. Xiao, J., Zou, S., Yu, K. Q., & Zheng, S. (2020). High-temperature mechanical behavior of 3D printed concrete elements. *Construction and Building Materials*, 265, 120320.
22. Nematollahi, B., Sanjayan, J., & Shaikh, F. U. A. (2017). Synthesis of geopolymer printable binders incorporating industrial solid wastes. *Minerals*, 7(12), 227.
23. Chen, Y., Jansen, K., Zhang, H., & Rodriguez, C. (2020). Extrusion mechanics and buildability metrics for ceramic concrete print heads. *Automation in Construction*, 119, 103340.
24. Keita, E., Bessaies-Bey, H., Zuo, W., & Roussel, N. (2019). Interlayer moisture retention and bond strength development in extruded concrete. *Cement and Concrete Research*, 123, 105780.
25. Weng, Y., Li, M., Tan, M. J., & Qian, S. (2018). Design and structural performance of 3D printed ceramic reinforced concrete structural elements. *Materials & Design*, 157, 476-486.
26. Ting, G. H. A., Tay, Y. W. D., & Tan, M. J. (2021). Life cycle assessment of 3D concrete printing vs conventional construction methods. *Journal of Cleaner Production*, 297, 126653.
27. Rashad, A. M. (2019). Waste ceramic powder as cement replacement: An overview. *Construction and Building Materials*, 211, 1121-1140.
28. Mohseni, E., Khotbehsara, M. M., & Naseri, F. (2016). Microstructure and

- mechanical evaluation of ceramic waste inclusion in sustainable cementitious mortars. Measurement, 84, 75-84.
29. Kruger, J., Zeranka, S., & van Zijl, G. (2020). Tribology and pumpability of aggregate-filled 3D printable concrete inks. Construction and Building Materials, 262, 120010.
 30. Wolfs, R. J. M., Bos, F. P., & Salet, T. A. M. (2018). Early age mechanical behavior of 3D printed concrete: Numerical modeling and experimental validation. Cement and Concrete Research, 106, 103-116.
 31. [Silfwerbrand, J. (2020). Multi-material additive manufacturing in structural civil engineering. Structural Concrete, 21(5), 1890-1899.
 32. ACI Committee 564. (2022). Guide to 3D Printing with Cementitious Materials (ACI 564R-22). American Concrete Institute, Farmington Hills, MI.

***Author for Correspondence**

Ananya V. Mukherjee

E-mail: ananya.mukherjee348@gmail.com

¹Associate Professor, Department of Civil Engineering, JIS College of Engineering

²Research Scholar, Department of Civil Engineering, JIS College of Engineering

³Research Scholar, Department of Civil Engineering, JIS College of Engineering

Received Date: May 03, 2026

Accepted Date: May 17, 2026

Published Date: May 29, 2026

Citation: Ananya V. Mukherjee, Priyanshu Verma, Debashish Banerjee. Advanced 3D-Printed Ceramic–Concrete Composite Materials for Next-Generation Sustainable Construction. Journal of Ceramics and Concrete Technology. 2026; 11(2): 74-86p.