MANTECH Publications

Journal of Ceramics and Concrete Technology
Volume 7 Issue 3
ISSN: 2457-0826 (Online)

Lab Study of Cement's Partial Substitution with Jute and Nylon Fibres in a Mix Design of Modified Concrete

Dr. Rakesh Panchal[1], Subhash Mohara[2]

Professor[1], Student[2]

Department of Civil Engineering

Prof. Ram Meghe Institute of Technology and Research, Badnera - Amravati, India

Corresponding Author's Email: *subhashmohara784@gmail.com[2]*

Abstract

This paper looks at commercially available synthetic fibres, particularly nylon and jute fibre. The weight of the fibres was varied from 0% to 1.0% of the weight of the cement for measuring compressive strength.

Keywords:- *Fibre, Nylon, Cement, Sand coarse*

INTRODUCTION

Concrete is typically made out of cement, sand, and gravel. In this course, granular material placed in a hard matrix of material with binder is employed (Cement). Fine granular materials occupy the space between coarse granular materials (sand).

The basic steps involved are summarized as follows:

- The fundamental purpose of this thesis is to look at potential methods for improving the properties of fiber-reinforced concrete.
- Investigate the usage of Jute and Coir Fiber in concrete.
- Calculate the average target quality using the determined trademark quality and the quantity of value control.
- Based on coarse and fine aggregate qualities, determine the relative extent of fine and coarse aggregates.
- Determine the concrete mix proportions for the first experimental batch

LITREATURE REVIEW

M.G.Alberti Et Al (2017)

were assumed The superiority of self-compacting polyolefin fibre reinforced cement has been established in both the fresh and solidified phases. Large residual

Page 123-128 © MANTECH PUBLIATIONS 2022. All Rights Reserved

features, most notably massive misshapenness, occur from post-splitting behaviour.

Flexural residual quality might be increased by using a small number of steel-snared filaments to correct slight misshapenness, resulting in a crossover fiber-strengthened solid appropriate for basic applications. Four varieties of ordinary fiber-strengthened cement with steel and polyolefin filaments were offered as a reference to a comparable self-compacting concrete. These solid mixes were made independently, with the same fibre material used for two escalating half-and-half combinations. Despite the assessment of crispness and mechanical properties, flexural and uniaxial break tests were carried out.

The analysis uncovered two partnerships (two types of strands working together to generate the break) as well as an improvement in the orientation and circulation of the filaments on the fracture surface.

It Was Assumed By Jun-Moyang Et Al. (2017)
that "this investigation will look into the effects of indistinct metallic filaments on the mechanical and long-term properties of solid asphalt. Two distinct sizes of shapeless metallic strands were mixed into the cement, and plain cement without filaments was also used as a control. The results of the tests revealed that adding the strands enhanced the general mechanical characteristics of cement, and the improvement increased as the number of filaments increased.

Fusing the shapeless metallic filaments raised the equivalent flexural quality and flexural quality proportion considerably. This may allow for a reduction in the thickness of the landing strip solid asphalt. The application of opaque metallic filaments improved the resistance of solid asphalt against surface cracking induced by repeated wheel stacking. In addition, incorporating 5 kg/m3 and 10 kg/m3 amorphous metallic filaments into solid asphalt resulted in 1.2 and 3.2 times longer usable lifetimes, respectively, as compared to their partner (plain concrete).

According to an actual life cycle cost analysis, the use of shapeless metallic threads in solid asphalt showed practical in terms of decreasing the life cycle cost when compared to plain solid asphalt, especially in heavy traffic situations.

Page 123-128 © MANTECH PUBLIATIONS 2022. All Rights Reserved

According To Jong-Hanlee Et Al. (2017), In a test investigation, the effects of solid quality and fibre content percentage on the flexural limit of steel fiber-strengthened cement were explored. Three fibre volume sections of 0.25, 0.375, and 0.5% were evaluated, as well as three cement compressive grades of 25, 35, and 45 MPa. The pressure and redirection relationship, initial pinnacle and post-breaking quality, and vitality intake limit were evaluated for the distinction in the fibre volume component and solid quality.

The findings revealed that the equal flexural quality %, which is defined by the main pinnacle quality and vitality intake limit, improved with increasing fibre volume but dropped with higher solid quality. Furthermore, the consequences of solid quality and fibre content % in a steel fiber-fortified solid floor chunk are explored. A final flexural limit also required evaluation of the impact of steel fibre material % and concrete composite network quality.

It Was Assumed By Mohsen Ahmadi Et Al. (2017) that

"MRA (Blended Recycled Aggregates) is a mix of recycled cement and brick work components. These totals are of inferior quality and consume more water than typical totals.

As a result, the solid with reused totals has a worse quality than the solid with regular totals. Using steel strands recovered from waste tyres in a solid with reused totals improves the solid's mechanical properties while also resolving the natural issue of these waste steel wires. The impact of reused steel filaments on the mechanical properties of normal cement and the solid with reused total is now being studied.

The influence of filaments on solid asphalt thickness decrease is also addressed. With fibre rates of 0.5 and 1% of solid volume, common coarse total substitution values are 0, 50, and 100%. Fundamental results reveal that incorporating reused filaments into a solid with reused entire seals decreases basic cement production by half the total substitution. Furthermore, inserting reused strands into the solid volume by 0.5 and 1% decreases solid asphalt thickness by 8 and 16%, respectively.

According To T.Simoes Et Al. (2017),


"the fundamental purpose of the current investigation is to examine how the solid compressive quality and shape of the steel filaments affect the conduct of the

Page 123-128 © MANTECH PUBLIATIONS 2022. All Rights Reserved

fiber/network interface." At this stage, three separate solid frameworks with 20, 60, and 100 MPa were planned, and two types of steel strands (Dramix®3D and Dramix®5D) were supported.


Explicit draw out examples were supplied, as well as three configurations of hub tractable tests with varying filaments (3D strands, and 3D and 5D strands with cut finishes). To broaden the scope of the exploratory test findings, a numerical model was aligned and used. Solid compressive equality is quite likely to have a direct impact on fiber/network quality. As a result of the snare created ends, higher quality was acquired in the set with untrimmed 3D filaments, moving anywhere between 64% and 72% of the total weight. Improving the attachment and erosion capabilities of filament switch straight ends by increasing their width and length.

RESULT AND CONCLUSION



	1	2	3	4	5	6
7 days(N/mm2)	17.78	18.37	18.96	19.56	22.07	21.04
14 days (N/mm2)	21.93	22.22	23.41	24.30	26.81	24.44
28 days (N/mm2)	25.93	26.52	27.41	28.44	30.96	28.89


Fig.1:-Results of jute fiber compressive strength test on M20



	CC	0.2	0.4	0.6	0.8	1
7 days(N/mm2)	17.78	19.41	20.00	20.59	21.19	20.30
14 days (N/mm2)	21.93	23.26	23.85	24.89	25.63	24.15
28 days (N/mm2)	25.93	28.15	28.74	29.78	31.11	29.33


Fig.2:-Results of Nylon fiber compressive strength test on M-20

Page 123-128 © MANTECH PUBLIATIONS 2022. All Rights Reserved



	CC	0.2	0.4	0.6	0.8	1
7 days(N/mm2)	19.85	20.52	21.41	22.67	22.81	21.70
14 days (N/mm2)	27.26	27.93	28.81	29.70	27.56	26.22
28 days (N/mm2)	31.85	32.15	33.19	34.96	33.19	31.78

Fig.3:-Results of jute fiber compressive strength test on M-25



	CC	0.2	0.4	0.6	0.8	1
7 days(N/mm2)	19.85	21.33	22.07	23.19	22.67	20.89
14 days (N/mm2)	27.26	28.89	29.78	30.89	29.63	27.85
28 days (N/mm2)	33.04	33.04	34.37	35.26	33.33	31.85

Fig.4:-Results of Nylon fiber compressive strength test on M25

CONCLUSION

- The compressive strength of Jute fibre increases as compared to normal concrete. After 7 days, 14 days, and 28 days of curing, the levels increase to 0.8% and then decrease as jute fibre is replaced by cement.

- The compressive strength of cement is increased when 0.8% Jute fibre is added.

- The compressive strength of M-20 grade concrete is increased by 16.246% in 28 days when 0.8% Jute fibre is substituted for cement.

- The compressive strength of M-25 grade concrete is increased by 8.895% in 28 days when 0.8% Jute fibre is substituted for cement.

- The compressive strength of Nylon fibre increases as compared to

Page 123-128 © MANTECH PUBLIATIONS 2022. All Rights Reserved

traditional concrete. After 7 days, 14 days, and 28 days of curing, the values obtained rise to 0.6% and then fall as more Nylon fibre is replaced by cement.

- The compressive strength is increased when 0.6% Nylon fibre is added to the cement.

REFERENCES

1. Simões, T., Octávio, C., Valença, J., Costa, H., Dias-da-Costa, D., &Júlio, E. (2017). Influence of concrete strength and steel fibre geometry on the fibre/matrix interface. Composites Part B: Engineering, 122, 156-164.

2. Alberti, M. G., Enfedaque, A., & Gálvez, J. C. (2017). Fibre reinforced concrete with a combination of polyolefin and steel-hooked fibres. Composite Structures, 171, 317-325.

3. Ahmadi, M., Farzin, S., Hassani, A., & Motamedi, M. (2017). Mechanical properties of the concrete containing recycled fibers and aggregates. Construction and Building Materials, 144, 392-398.

4. Yang, J. M., Shin, H. O., & Yoo, D. Y. (2017). Benefits of using amorphous metallic fibers in concrete pavement for long-term performance. Archives of civil and mechanical engineering, 17(4), 750- 760.

5. Lee, J. H. (2017). Influence of concrete strength combined with fiber content in the residual flexural strengths of fiber aggregates. Construction and Building Materials, 144, 392-398

Page 123-128 © MANTECH PUBLIATIONS 2022. All Rights Reserved