MANTECH Publications

Journal of Research in Physics and Applied Sciences
Volume 8, Issue 1, January-June 2025

Nanomaterials for Enhanced Thermoelectric Energy Conversion: Synthesis, Characterization, and Applications in Industrial Waste Heat Recovery

Dr. Shubham Kumar
Assistant Professor
Department of Applied Physics
Girijabai Sail Institute of Technology
Email id: *shubhamkumar.rs@gmail.com*

Neha Iyer
Student
Department of Applied Physics
Girijabai Sail Institute of Technology
Email id: *neha.nano@yahoo.com*

Ritesh Verma
Student
Department of Applied Physics
Girijabai Sail Institute of Technology
Email id: *riteshverma@rediffmail.com*

Abstract

Thermoelectric energy conversion presents a promising route for transforming waste heat into usable electrical energy, addressing both energy efficiency and sustainability concerns. The efficiency of thermoelectric devices is largely governed by the dimensionless figure of merit (ZT), which depends on the material's Seebeck coefficient, electrical conductivity, and thermal conductivity. Nanostructured materials have shown immense potential in optimizing these properties simultaneously, thus enhancing thermoelectric performance. This paper provides a comprehensive review and analysis of various nanomaterials synthesized for thermoelectric applications, detailing the synthesis techniques, characterization methods, and material modifications

 Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

that contribute to improved energy conversion. Additionally, it explores the practical application of these materials in industrial waste heat recovery systems, emphasizing the scalability, integration challenges, and future research directions.

Keywords: *Thermoelectric materials, Nanostructures, Waste heat recovery, ZT enhancement, Seebeck coefficient, Thermal conductivity, Synthesis and characterization*

INTRODUCTION

Thermoelectric energy conversion has gained considerable attention due to its ability to convert temperature gradients directly into electrical voltage. This capability is particularly useful in harnessing waste heat from industrial processes, where a significant portion of energy is lost as low-grade heat. The performance of thermoelectric materials is quantified by the dimensionless figure of merit $ZT = S^2\sigma T/\kappa$, where S is the Seebeck coefficient, σ is the electrical conductivity, T is the absolute temperature, and κ is the thermal conductivity.

Achieving high ZT values requires balancing these interdependent properties, which poses a substantial materials engineering challenge.

Recent advances in nanotechnology have opened new pathways for enhancing thermoelectric performance. Nanostructuring can reduce lattice thermal conductivity without severely affecting electrical conductivity or the Seebeck coefficient. This paper aims to explore the synthesis, structural manipulation, and characterization of nanomaterials designed to improve thermoelectric efficiency. Particular focus is placed on the feasibility of deploying these materials in real-world industrial waste heat recovery systems.

Principles of Thermoelectric Energy Conversion

The thermoelectric effect refers to the direct conversion of temperature differences to electric voltage and vice versa. This phenomenon encompasses three key effects: the Seebeck effect, the Peltier effect, and the Thomson effect. Among these, the Seebeck effect is most critical for power generation applications. The Seebeck effect describes the generation of an electromotive force (emf) across a thermoelectric material when a temperature gradient exists

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

between its two ends. This emf results from the diffusion of charge carriers (electrons or holes) from the hot side to the cold side of the material, thereby generating a voltage difference.

The Peltier effect, in contrast, involves the absorption or emission of heat when an electric current flows across the junction of two different conductors or semiconductors. This effect is utilized in thermoelectric cooling applications. The Thomson effect describes the generation or absorption of heat along a single conductor carrying a current when subjected to a temperature gradient. While all three effects are rooted in the same physical principles, the Seebeck effect is primarily exploited in thermoelectric generators used for energy conversion from heat to electricity.

The performance of a thermoelectric material is determined by its dimensionless figure of merit, ZT, which is given by the equation $ZT = S^2\sigma T/\kappa$, where S is the Seebeck coefficient, σ is the electrical conductivity, T is the absolute temperature, and κ is the total thermal conductivity (including both lattice and electronic contributions). A high ZT value indicates better thermoelectric performance and higher conversion efficiency.

One of the main challenges in enhancing ZT is the interdependence of its constituent parameters. For instance, increasing electrical conductivity often results in increased electronic thermal conductivity, which is undesirable. Similarly, improving the Seebeck coefficient may compromise electrical conductivity. This coupling makes it difficult to improve ZT through traditional bulk material optimization. Nanostructuring offers a potential solution to this challenge by enabling independent tuning of these properties through control over phonon scattering, carrier concentration, and energy filtering mechanisms.

Nanomaterials, with their unique ability to scatter phonons while maintaining high charge carrier mobility, provide a strategic pathway to break the conventional trade-offs among thermoelectric parameters and enhance the overall energy conversion efficiency.

Synthesis Techniques of Nanomaterials for Thermoelectrics

The synthesis of nanomaterials for thermoelectric applications is a critical step in achieving materials with desirable electrical and thermal transport properties. Various synthesis

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

techniques have been developed to fabricate nanostructured thermoelectric materials, each with specific advantages concerning scalability, particle size control, uniformity, and cost-effectiveness. These techniques are tailored to produce a variety of nanostructures, including nanowires, nanotubes, nanoparticles, quantum dots, superlattices, and nanocomposites.

One widely used synthesis technique is the sol-gel method. This method involves the transition of a solution system from a liquid "sol" into a solid "gel" phase. The sol-gel process offers excellent compositional control and is particularly suitable for oxide-based thermoelectric materials. It enables low-temperature processing and uniform mixing of precursors at the molecular level, making it ideal for fabricating homogeneous and fine-grained nanostructures.

Hydrothermal and solvothermal synthesis techniques involve the use of high-temperature and high-pressure aqueous or non-aqueous solutions, respectively, to grow crystalline nanostructures. These methods are advantageous for producing uniform nanoparticles with controlled morphologies. They are particularly suitable for synthesizing bismuth telluride, zinc oxide, and other chalcogenide-based thermoelectric materials. The ability to precisely control temperature, pressure, and reaction time allows for fine-tuning of particle size and shape.

Chemical vapor deposition (CVD) is another popular technique used for the synthesis of thin films and nanowires. In CVD, gaseous precursors react or decompose on a heated substrate to form a solid material. This method provides excellent control over film thickness and composition, and it is capable of producing highly pure and uniform nanostructures. CVD is extensively used for fabricating silicon-germanium nanowires and superlattice structures for high-performance thermoelectrics.

Mechanical alloying and ball milling are top-down approaches that involve repeated welding, fracturing, and re-welding of powder particles in a high-energy ball mill. These techniques are relatively simple and cost-effective for producing bulk nanostructured materials. They are especially useful for preparing nanocomposites and alloys by incorporating secondary phases or doping elements to enhance thermoelectric properties. The resultant powders can be further densified using sintering methods.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

Molecular beam epitaxy (MBE) is a highly controlled technique for growing epitaxial layers with atomic-scale precision. It involves the deposition of atomic or molecular beams onto a heated substrate under ultra-high vacuum conditions. MBE is used to fabricate quantum wells, superlattices, and heterostructures with precise control over layer thickness and composition. Although expensive and less scalable, MBE is invaluable for fundamental studies and prototype development of thermoelectric nanostructures.

Spark plasma sintering (SPS) is a rapid densification technique used to consolidate nanopowders into bulk nanostructured materials. It applies pulsed direct current and pressure to the powder, enabling fast heating rates and short processing times. SPS preserves the nano features of the initial powders and improves the mechanical integrity and electrical connectivity of the final product. It is widely used in the fabrication of nanocomposites and heavily doped semiconductors.

These synthesis techniques can be employed individually or in combination to fabricate advanced nanostructured thermoelectric materials. The choice of synthesis method directly influences the crystallinity, grain size, phase purity, and defect concentration of the material, which in turn affects the thermoelectric performance.

For example, sol-gel and hydrothermal methods are excellent for controlled nanoparticle synthesis, while CVD and MBE are better suited for thin films and layered nanostructures. Ball milling and SPS provide a route for scalable production of bulk nanocomposites with tailored microstructures.

An integrated approach combining synthesis with post-processing techniques such as doping, annealing, and surface modification is often employed to fine-tune the electrical and thermal transport properties of thermoelectric materials. The ultimate goal is to engineer nanomaterials with optimized carrier concentration, enhanced phonon scattering, and minimal grain boundary resistance, thereby maximizing the figure of merit and enabling their practical deployment in thermoelectric generators for industrial waste heat recovery.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

Table 1: Common Synthesis Methods for Thermoelectric Nanomaterials and Their Advantages

Synthesis Method	**Advantages**	**Typical Materials Synthesized**
Sol-gel	Low-temperature process, good compositional control	Oxide-based thermoelectrics
Hydrothermal	Uniform nanoparticles, scalable	Bi_2 Te_3 , ZnO
CVD	High purity, thin films	SiGe nanowires, superlattices
Ball milling	Simple, cost-effective	Bulk nanocomposites
MBE	Atomic layer control, high precision	Superlattice structures
SPS	Rapid densification, retains nano features	Nanocomposite pellets

Characterization Techniques for NanostructuredThermoelectric Materials

Characterizing nanostructured thermoelectric materials is a fundamental step in both research and industrial development to ensure that the materials exhibit the desired structural, compositional, and functional properties. Because thermoelectric performance depends on a delicate balance between electrical conductivity, thermal conductivity, and the Seebeck coefficient, it is essential to use multiple complementary techniques for a holistic understanding of material behavior. These techniques are broadly classified into three categories: structural characterization, compositional analysis, and thermoelectric property evaluation.

Structural characterization focuses on determining the physical architecture and crystalline structure of the synthesized nanomaterials. One of the most widely used techniques for this purpose is X-ray diffraction (XRD). XRD provides information on the crystalline phases present, lattice parameters, grain sizes, and crystal orientation. It helps confirm whether the desired compound has formed and can detect impurities or secondary phases that may negatively influence thermoelectric properties. Sharp and well-defined diffraction peaks indicate high crystallinity, which is often associated with good electrical conductivity, while peak broadening can suggest the presence of nanoscale grains or structural disorder.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

Scanning electron microscopy (SEM) is employed to observe the surface morphology of the material. SEM reveals details about grain size, porosity, surface roughness, and particle agglomeration. These features are particularly important in nanostructured thermoelectrics because surface area and grain boundaries play a vital role in phonon scattering and carrier mobility. SEM imaging can also be used to verify the success of sintering or film deposition processes.

For even higher resolution analysis of internal structure, transmission electron microscopy (TEM) is utilized. TEM enables direct imaging of lattice fringes, defects, and nanostructures such as quantum dots or superlattice layers. High-resolution TEM (HRTEM) can be used to investigate dislocation networks and interface quality in composite materials.

Moreover, selected area electron diffraction (SAED) patterns obtained through TEM provide additional crystallographic information at the nanoscale, making this technique invaluable for correlating structural features with thermoelectric behavior.

Compositional analysis is critical to confirm the stoichiometry and elemental distribution within the sample. Energy-dispersive X-ray spectroscopy (EDX), which is often integrated with SEM or TEM systems, provides elemental mapping and quantitative analysis of constituent elements. It helps ensure that the intended doping elements are uniformly distributed and identifies any contamination or non-uniformity in the sample.

X-ray photoelectron spectroscopy (XPS) is used to analyze the chemical states of the elements on the material's surface. XPS offers high surface sensitivity and is essential for detecting oxidation states, binding energies, and chemical interactions at grain boundaries or interfaces.

Surface chemistry has a significant influence on carrier scattering and energy filtering effects, especially in nanocomposites and layered materials.

Thermoelectric property evaluation involves direct measurement of the functional parameters that determine the figure of merit (ZT). The Seebeck coefficient, a measure of the voltage generated in response to a temperature gradient, is typically measured using a dedicated Seebeck measurement setup.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

This setup involves maintaining a temperature gradient across the sample and measuring the corresponding voltage using sensitive voltmeters. High Seebeck coefficients are desirable for good thermoelectric performance and are often enhanced in nanostructured materials due to energy-dependent carrier scattering.

Electrical conductivity is commonly measured using the four-probe method. This technique eliminates the effects of contact resistance, providing accurate measurement of intrinsic electrical transport. A current is passed through the outer two probes while the voltage is measured across the inner two, allowing precise calculation of resistivity. Electrical conductivity data is crucial for assessing the carrier mobility and the impact of grain boundaries or interfaces introduced during nanostructuring.

Thermal conductivity is assessed using laser flash analysis, a non-contact method where a short laser pulse heats one side of the sample and the temperature rise is measured on the opposite side. The time taken for heat to travel through the sample is used to calculate thermal diffusivity, which, when combined with specific heat and density, yields the thermal conductivity.

This technique is particularly useful for nanomaterials where phonon scattering mechanisms are complex and often dominant. Nanostructures typically exhibit lower thermal conductivity due to increased phonon-boundary scattering, which enhances thermoelectric efficiency.

Together, these characterization techniques provide comprehensive insights into the relationships between synthesis conditions, nanostructure features, and thermoelectric properties. Structural and compositional analyses ensure the quality and integrity of the materials, while property evaluation confirms their suitability for thermoelectric applications. The integration of these methods allows researchers and engineers to design and optimize nanostructured thermoelectric materials that offer superior performance for practical applications such as waste heat recovery in industrial systems.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved




Figure 1: Workflow for Synthesis and Characterization of Thermoelectric Nanomaterials

Effect of Nanostructuring on Thermoelectric Properties

Nanostructuring has emerged as a transformative strategy for significantly improving the performance of thermoelectric materials. The central idea behind this approach is to manipulate the transport properties of heat and charge carriers by introducing structural features at the nanoscale. These engineered nanostructures, including nanograins, quantum dots, and layered superlattices, alter the fundamental mechanisms by which phonons and electrons traverse the material, thereby decoupling the traditionally interdependent properties of electrical and thermal conductivity.

One of the primary goals of nanostructuring is to suppress lattice thermal conductivity without adversely affecting electrical conductivity. This is achieved through enhanced phonon scattering at grain boundaries, interfaces, and defects. In a bulk material, phonons—the main carriers of heat—travel relatively unimpeded. However, in a nanostructured material, the presence of numerous boundaries causes frequent phonon collisions, which disrupt heat flow and reduce the thermal conductivity. This phenomenon, often described as phonon boundary scattering, is highly effective in lowering the denominator of the figure of merit (ZT), thereby enhancing thermoelectric performance.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

Another vital mechanism enabled by nanostructuring is carrier filtering. In this context, energy barriers at interfaces or grain boundaries selectively allow high-energy charge carriers to pass while blocking low-energy ones. This increases the average energy of the carriers and thereby improves the Seebeck coefficient, which is a measure of the voltage produced per unit temperature difference. Higher Seebeck coefficients are directly linked to improved voltage output and overall efficiency of thermoelectric generators.

Grain boundary engineering is also crucial in nanostructured materials. By carefully controlling the size, distribution, and orientation of grains, it is possible to fine-tune the balance between electrical and thermal transport. Grain boundaries can impede electron movement, which lowers electrical conductivity, but they can also reduce thermal conductivity more significantly. The key is to engineer these boundaries in such a way that phonon scattering is maximized while electron scattering is minimized. This selective control over carrier transport is one of the main advantages of nanostructuring over conventional bulk material design.

In summary, nanostructuring offers a powerful approach to overcoming the limitations of traditional thermoelectric materials. By exploiting size effects, interface phenomena, and energy filtering mechanisms, researchers can develop materials with enhanced ZT values, bringing thermoelectric devices closer to practical and efficient deployment in energy recovery systems.

Prominent Nanomaterials for Thermoelectric Applications

A number of nanostructured materials have emerged as leading candidates for thermoelectric applications due to their unique structural features and promising transport properties. Each of these materials has a specific operational temperature range and is suitable for different application environments, especially in industrial waste heat recovery.

Bismuth telluride (Bi_2 Te_3) nanostructures are among the most well-established thermoelectric materials and are particularly effective near room temperature. NanostructuringBi_2 Te_3 into thin films, nanowires, or nanocomposites significantly reduces its thermal conductivity while maintaining or enhancing its electrical performance. These

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

materials are widely used in commercial Peltier cooling modules and low-grade heat recovery systems.

Silicon-germanium (SiGe) nanowires represent another key category of thermoelectric nanomaterials, especially suitable for high-temperature applications such as space power generation and industrial heat recovery. The nanowire configuration provides extensive phonon scattering, resulting in a drastic reduction in lattice thermal conductivity, while high electron mobility ensures sufficient electrical conductivity.

Lead telluride (PbTe) quantum dots have demonstrated exceptional performance in mid- to high-temperature ranges. The introduction of nanoscale inclusions and embedded nanostructures in PbTe matrices increases phonon scattering and enhances carrier filtering. These mechanisms result in high ZT values, particularly when synergized with heavy element doping or hybrid nanocomposite approaches.

Skutterudites are complex crystal structures often enhanced with nanoprecipitates. These materials are effective thermoelectrics in the temperature range of 500–800 K. Nanoprecipitates within the skutterudite matrix scatter heat-carrying phonons while leaving electrical conductivity relatively unaffected. The inclusion of rare-earth elements or other heavy atoms in the voids of the skutterudite lattice further enhances performance.

Oxide-based nanocomposites, such as $Ca_3\ Co_4\ O_9$, offer a more environmentally friendly alternative to traditional thermoelectrics. These materials are chemically stable at high temperatures and can be synthesized using cost-effective methods. Although their thermoelectric efficiency is generally lower than chalcogenides, ongoing research in nanostructuring and doping is closing the performance gap, making them suitable for sustainable energy applications.

Each of these nanomaterials brings unique advantages depending on the intended application environment. Their tunable properties through nanostructuring open new pathways for designing efficient and reliable thermoelectric generators across a wide range of temperatures.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

Application in Waste Heat Recovery Systems

The industrial sector accounts for a significant proportion of global energy consumption, and a substantial portion of this energy is lost as waste heat during various processes such as metal smelting, chemical production, glass manufacturing, and power generation. Thermoelectric generators (TEGs) offer a clean, compact, and scalable solution to recover this otherwise wasted energy and convert it into useful electrical power.

The integration of thermoelectric modules into industrial systems begins with strategic design considerations. A key factor is the operating temperature of the waste heat source. The chosen thermoelectric material must be stable and efficient within that temperature range. For instance, Bi_2Te_3 may be suitable for lower temperature waste heat sources such as exhaust air, while PbTe or SiGe is preferred for higher temperature streams like furnace flue gases.

Thermal interface materials play an essential role in maximizing heat transfer between the industrial surface and the thermoelectric module. Poor thermal contact can lead to significant energy losses and reduced device efficiency. Effective module packing and assembly techniques are also critical to ensure structural integrity and thermal conductivity under harsh industrial conditions.

Another important component of waste heat recovery systems is the power electronics used to manage and condition the electrical output from TEGs. Since thermoelectric devices produce low voltages, boost converters and voltage regulators are often required to match the output to the grid or a local energy storage system.

Thermoelectric modules can be mounted directly onto hot surfaces such as boilers, ducts, or chimneys. Modular design allows for scalability, enabling engineers to tailor installations to specific plant layouts and heat sources. By capturing and converting even a small fraction of industrial waste heat, thermoelectric systems can lead to significant energy savings, reduced greenhouse gas emissions, and improved overall energy efficiency.

CHALLENGES AND LIMITATIONS

While the prospects for nanostructured thermoelectric materials are promising, several practical challenges must be addressed to facilitate their widespread adoption in industrial

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

energy systems. One of the foremost issues is scalability. Many synthesis techniques that yield high-performance nanostructures are difficult to scale up economically for mass production. Processes such as molecular beam epitaxy or chemical vapor deposition are precise but cost-intensive and slow.

The thermal and mechanical stability of nanostructured materials under prolonged exposure to high temperatures and thermal cycling is another concern. Many nanostructures degrade or undergo phase changes over time, which leads to performance deterioration. Developing robust materials that maintain their structure and performance over long operational lifetimes is essential.

Toxicity and environmental concerns also limit the use of certain high-performance materials. Elements such as lead and tellurium, commonly found in PbTe and Bi_2 Te_3 , raise issues related to safety and environmental impact. Regulations and public pressure are increasingly pushing for the development of green thermoelectric materials composed of earth-abundant and non-toxic elements.

Integration with existing industrial systems can also be complex. Retrofitting thermoelectric modules to legacy equipment may involve technical modifications and logistical challenges. There is also a need for compatible power electronics and control systems that can dynamically respond to varying temperature conditions.

Addressing these limitations requires a multi-disciplinary approach, combining expertise from material science, mechanical engineering, thermal management, environmental science, and process engineering. Collaborative efforts across academia, industry, and policy-making are essential to overcome these hurdles and make thermoelectric waste heat recovery a viable and impactful technology.

Future Outlook and Research Directions

The future of nanostructured thermoelectric materials lies in overcoming current limitations and exploring innovative approaches that merge material innovation with system-level integration. One of the most promising research directions is the development of eco-friendly, earth-abundant thermoelectric materials. Compounds based on magnesium, tin, iron, and

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

cobalt are being actively investigated for their non-toxic nature and potential to achieve high ZT values with appropriate nanostructuring.

High-throughput synthesis and screening techniques, powered by automation and artificial intelligence, are accelerating the discovery of new thermoelectric materials. These methods allow rapid exploration of vast compositional and structural spaces, identifying optimal candidates with minimal experimental effort.

Multiscale modeling and simulation are becoming integral to thermoelectric material design. These tools enable researchers to predict the thermoelectric behavior of materials based on atomic, nanoscale, and mesoscale phenomena. By integrating computational models with experimental data, it is possible to fine-tune nanostructures for maximum performance.

Another emerging trend is the development of hybrid energy systems that combine thermoelectrics with other renewable technologies such as photovoltaics or biomass energy. These integrated systems can offer enhanced energy harvesting capabilities and resilience in variable industrial environments.

Finally, industrial-scale pilot demonstrations are critical to validate laboratory-scale findings and encourage broader adoption. Demonstrating cost savings, energy efficiency improvements, and operational reliability under real-world conditions will help build confidence in thermoelectric technology among industry stakeholders.

In conclusion, the journey toward widespread deployment of nanostructured thermoelectrics for waste heat recovery is both challenging and exciting. Continued research, innovation, and collaboration will pave the way for thermoelectric technologies to play a significant role in the global transition toward sustainable and efficient energy systems.

CONCLUSION

Nanomaterials offer a transformative opportunity to enhance thermoelectric energy conversion by manipulating phonon and electron transport at the nanoscale. Their ability to achieve high ZT values opens the door for sustainable waste heat recovery in industrial systems. However, real-world application demands continued progress in scalable synthesis,

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

cost-effectiveness, and system-level integration. By addressing these challenges, thermoelectric nanomaterials could play a vital role in the global push for energy efficiency and carbon neutrality.

REFERENCES

1. Dresselhaus, M. S., Chen, G., Tang, M. Y., Yang, R. G., Lee, H., Wang, D. Z., ... & Ren, Z. F. (2007). New directions for low-dimensional thermoelectric materials. *Advanced Materials, 19*(8), 1043–1053. https://doi.org/10.1002/adma.200600527
2. Heremans, J. P., Thrush, C. M., & Morelli, D. T. (2004). Thermopower enhancement in lead telluride nanostructures. *Physical Review B, 70*(11), 115334. https://doi.org/10.1103/PhysRevB.70.115334
3. Poudel, B., Hao, Q., Ma, Y., Lan, Y., Minnich, A., Yu, B., ... & Ren, Z. (2008). High-thermoelectric performance of nanostructured bismuth antimony telluride bulk alloys. *Science, 320*(5876), 634–638. https://doi.org/10.1126/science.1156446
4. Vineis, C. J., Shakouri, A., Majumdar, A., &Kanatzidis, M. G. (2010). Nanostructured thermoelectrics: Big efficiency gains from small features. *Advanced Materials, 22*(36), 3970–3980. https://doi.org/10.1002/adma.201000839
5. Zhao, L. D., Lo, S. H., Zhang, Y., Sun, H., Tan, G., Uher, C., ... &Kanatzidis, M. G. (2014). Ultralow thermal conductivity and high thermoelectric figure of merit in SnSe crystals. *Nature, 508*(7496), 373–377. https://doi.org/10.1038/nature13184
6. Goldsmid, H. J. (2010). *Introduction to thermoelectricity*. Springer Series in Materials Science, Vol. 121. https://doi.org/10.1007/978-3-642-00716-3
7. Harman, T. C., Taylor, P. J., Walsh, M. P., &Laforge, B. E. (2002). Quantum dot superlattice thermoelectric materials and devices. *Science, 297*(5590), 2229–2232. https://doi.org/10.1126/science.1072886
8. Wang, X., Xu, X., & Zhou, J. (2013). Recent progress in thermoelectric materials. *Chinese Physics B, 22*(8), 088202. https://doi.org/10.1088/1674-1056/22/8/088202
9. Snyder, G. J., &Toberer, E. S. (2008). Complex thermoelectric materials. *Nature Materials, 7*(2), 105–114. https://doi.org/10.1038/nmat2090
10. Bell, L. E. (2008). Cooling, heating, generating power, and recovering waste heat with thermoelectric systems. *Science, 321*(5895), 1457–1461. https://doi.org/10.1126/science.1158899

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved

11. Nielsch, K., Bachmann, J., Kimling, J., & Böttner, H. (2011). Thermoelectric nanostructures: From physical model systems towards nanograined composites. *Advanced Energy Materials, 1*(5), 713–731. https://doi.org/10.1002/aenm.201100205
12. Zhao, D., Tan, G., Hao, S., He, J., Wolverton, C., &Kanatzidis, M. G. (2016). Thermoelectrics with earth-abundant elements: High-performance Mg3Sb2-based materials. *Journal of the American Chemical Society, 138*(7), 2366–2373. https://doi.org/10.1021/jacs.5b12167
13. Dresselhaus, M. S., Lin, Y. M., Rabin, O., Black, M. R., Dresselhaus, G., & Ren, Z. F. (2003). Nanowires for thermoelectric applications. *Physics of the Solid State, 45*(7), 1148–1150. https://doi.org/10.1134/1.1586460
14. Zhang, Q., Sun, Y., Xu, W., & Zhu, D. (2014). Organic thermoelectric materials: Emerging green energy materials converting heat to electricity directly and efficiently. *Advanced Materials, 26*(40), 6829–6851. https://doi.org/10.1002/adma.201306294
15. Sootsman, J. R., Chung, D. Y., &Kanatzidis, M. G. (2009). New and old concepts in thermoelectric materials. *Angewandte Chemie International Edition, 48*(46), 8616–8639. https://doi.org/10.1002/anie.200900598
16. Bhattacharya, S., & Majumdar, A. (2012). Materials for low-temperature thermoelectric waste heat recovery. *Annual Review of Materials Research, 42*, 131–155. https://doi.org/10.1146/annurev-matsci-070511-155040
17. Zebarjadi, M., Esfarjani, K., Dresselhaus, M. S., Ren, Z. F., & Chen, G. (2012). Perspectives on thermoelectrics: From fundamentals to device applications. *Energy & Environmental Science, 5*(1), 5147–5162. https://doi.org/10.1039/C1EE02497C
18. Giri, A., Hopkins, P. E., & Beechem, T. E. (2016). Thermal conductivity tuning in nanomaterials via strain and size effects. *Nano Letters, 16*(9), 5432–5437. https://doi.org/10.1021/acs.nanolett.6b01880
19. Yang, J., & Caillat, T. (2006). Thermoelectric materials for space and automotive power generation. *MRS Bulletin, 31*(3), 224–229. https://doi.org/10.1557/mrs2006.49
20. Min, G., & Rowe, D. M. (2002). Experimental evaluation of alternative thermoelectric materials for power generation. *Journal of Power Sources, 109*(2), 452–455. https://doi.org/10.1016/S0378-7753 (02)00125-8.

Page 10-25 © MANTECH PUBLICATIONS 2025. All Rights Reserved