MANTECH Publications

Journal of Research in Physics and Applied Sciences
Volume 8, Issue 1, January-June 2025

Plasma-Assisted Surface Modification for Enhanced Industrial Coatings in Aerospace, Automotive, and Biomedical Applications

Harshit Anand
Assistant Professor
Department of Applied Sciences
Suryodaya College of Engineering & Technology
Email id: *harshitanand.research@gmail.com*

Sneha Verma
Assistant Professor
Department of Mechanical Engineering
Suryodaya College of Engineering & Technology
Email id: *snehaverma_mech@rediffmail.com*

Abstract

The advancement of industrial coatings has seen a paradigm shift with the integration of plasma-assisted surface modification techniques. Low-temperature plasma offers a versatile, energy-efficient, and environmentally friendly method to alter surface characteristics such as hardness, corrosion resistance, and adhesion without affecting bulk properties. This paper explores the underlying mechanisms of plasma-based surface engineering, its variants, and its significant implications for aerospace, automotive, and biomedical industries. A comprehensive discussion is presented on the plasma-material interaction, types of plasma treatments, equipment involved, process parameters, and the resulting microstructural and property modifications. Furthermore, the advantages and constraints of plasma-assisted technologies over conventional coating methods are analyzed. The paper also includes comparative data, case studies, and graphical illustrations to aid understanding of practical applications.

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

Keywords: *Plasma-assisted modification, industrial coatings, low-temperature plasma, surface hardness, corrosion resistance, adhesion, aerospace, automotive, biomedical applications.*

INTRODUCTION

Surface modification is a critical process in enhancing the lifespan and performance of industrial components by altering their surface properties without changing the underlying bulk material. Traditional methods like heat treatment, electroplating, or chemical vapor deposition come with limitations such as high temperature processing, environmental toxicity, and low precision. Plasma-assisted surface modification has emerged as a highly adaptable solution, capable of providing enhanced adhesion, hardness, wear, and corrosion resistance.

Low-temperature plasmas, due to their non-equilibrium nature, allow for precise control of energy input and surface interaction. This technology is gaining momentum particularly in sectors requiring advanced material durability and performance under extreme environments, such as aerospace turbines, automotive engine parts, and biomedical implants.

Plasma Science and Surface Interaction Mechanisms

Plasma, often referred to as the fourth state of matter, comprises ions, electrons, neutral atoms, and photons. When gases like argon, oxygen, nitrogen, or hydrogen are ionized under low pressure and subjected to electric fields, a plasma discharge is created. The interaction of this energetic environment with a material's surface can result in cleaning, etching, activation, cross-linking, and coating deposition.

Surface modifications primarily occur due to energetic ion bombardment, ultraviolet photon interaction, and radical-driven chemical reactions. The synergy of these phenomena leads to increased surface energy, modified roughness, altered surface chemistry, and even formation of thin functional films.

Types of Plasma Treatment Methods

Different configurations and plasma sources are employed depending on the end-use and material requirements:

1. Plasma Cleaning – Removes organic and inorganic contaminants

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

2. Plasma Etching – Tailors surface morphology through material removal
3. Plasma Activation – Enhances surface energy for improved adhesion
4. Plasma Polymerization – Deposits functionalized thin films for specific properties
5. Plasma Nitriding/Oxidation – Enhances hardness and corrosion resistance in metals

Table 1: Comparison of Plasma Treatment Methods and Their Primary Effects

Plasma Process	**Working Gas**	**Key Effect**	**Common Substrate**	**Industrial Use Case**
Plasma Cleaning	Oxygen, Argon	Surface contamination removal	Polymers, metals	Medical devices, electronics
Plasma Etching	CF_4 , O_2 , H_2	Controlled material removal	Silicon, ceramics	MEMS, sensors
Plasma Activation	Air, Oxygen	Increased surface energy	Polymers	Automotive, packaging
Plasma Polymerization	Hydrocarbon gases	Functional thin film coating	Metals, ceramics	Protective biomedical coatings
Plasma Nitriding/Oxidation	N_2 , NH_3 , O_2	Surface hardening, oxidation	Steel, titanium	Aerospace, automotive, surgical tools

Plasma-Assisted Hardness Enhancement

Low-temperature plasma-based surface treatment techniques such as plasma nitriding have gained considerable attention due to their remarkable ability to enhance surface hardness without compromising the bulk properties of the base material.

Plasma nitriding is a thermochemical process that involves the introduction of nitrogen ions into the surface of a metal, typically steel or titanium, in a controlled low-temperature plasma environment. This results in the formation of hard nitrides such as iron nitride (Fe_4 N, Fe_2 – $_3$ N) in steels or titanium nitride (TiN) in titanium alloys. These nitrides are known for their high hardness, excellent wear resistance, and thermal stability.

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

In contrast to conventional hardening methods that often require high-temperature processing and may lead to thermal distortion or grain coarsening, plasma nitriding operates at relatively low temperatures (typically between 350°C and 550°C), making it suitable for precision components. The depth of the nitrided layer can be controlled by adjusting treatment duration, gas composition, and plasma power, allowing customization based on application requirements.

This treatment is particularly vital in industries where components are exposed to repeated mechanical stress, sliding contact, or abrasive conditions. For example, in automotive systems, gears and camshafts benefit from increased surface hardness and wear resistance. In aerospace applications, plasma-hardened titanium alloys used in structural fasteners or engine parts show improved fatigue life and surface integrity. In biomedical fields, surgical tools such as bone chisels, scalpel blades, and dental instruments, which must withstand repeated sterilization and mechanical use, are often plasma-treated to improve their durability and reliability without altering their fine geometries.

In an experimental case, titanium specimens subjected to plasma nitriding for 4 hours at 500°C using nitrogen-hydrogen gas mixture showed an increase in surface hardness from 320 HV (Vickers Hardness) to 1150 HV, indicating a nearly fourfold improvement. This significant enhancement was achieved without compromising the internal toughness or introducing phase changes in the bulk metal.

Plasma-Induced Corrosion Resistance

Corrosion poses a serious challenge to the longevity and performance of metallic components used in harsh or variable environments. Traditional corrosion protection techniques such as painting, anodizing, or cathodic protection have limitations, especially when the surface is complex or requires biocompatibility. Plasma-based surface treatments, particularly plasma oxidation and plasma polymerization, have emerged as superior alternatives due to their ability to form dense, uniform, and defect-free coatings that act as highly effective barriers.

One of the most successful applications of this technique is Plasma Electrolytic Oxidation (PEO), which is commonly applied to aluminum and magnesium alloys. During this process,

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

the component is immersed in an electrolyte, and high-voltage plasma discharges are used to grow a thick, ceramic-like oxide layer on the metal surface.

This layer not only offers superior resistance to chemical attack and high temperatures but also improves wear and fatigue resistance. Such properties are especially beneficial in aerospace applications, where lightweight yet robust components are required to withstand extreme environmental conditions such as salt spray and temperature variations.

Similarly, plasma polymerization using precursor gases like hexamethyldisiloxane (HMDSO) or fluorocarbons results in ultra-thin hydrophobic or oleophobic films on metal and polymer substrates. These films repel water, oil, and other corrosive substances, significantly reducing corrosion rates in automotive and industrial machinery. In the automotive industry, plasma coatings are applied to underbody components, suspension parts, and fuel systems to extend service life and reduce maintenance needs.

Enhanced Adhesion through Surface Activation

In industrial coatings, the long-term performance of a coated component is heavily dependent on the adhesion strength between the coating and the substrate. Weak adhesion can result in delamination, blistering, or cracking under stress, temperature fluctuation, or environmental exposure. Plasma activation is an effective pre-treatment technique to improve surface adhesion by altering the surface chemistry and morphology of the substrate.

During plasma activation, high-energy species from the plasma bombard the substrate surface, breaking molecular bonds and creating new functional groups such as hydroxyl (-OH), carbonyl (-C=O), or amine (-NH_2) depending on the gas used. Oxygen, argon, or ammonia plasmas are commonly employed to treat polymeric surfaces such as polyethylene, polypropylene, and PTFE. This process results in increased surface energy and wettability, which enhances the bonding between the substrate and subsequent coatings like paints, adhesives, or inks.

In the medical industry, catheter tubes, implants, and prosthetics made of biocompatible polymers benefit from plasma treatment before receiving antimicrobial or drug-release coatings. The activated surface ensures strong adhesion without compromising

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

biocompatibility or structural integrity. Similarly, in the automotive sector, plastic dashboards and bumpers undergo plasma activation to ensure proper paint adhesion, improving aesthetic durability and safety.

Equipment and Process Parameters

The equipment used in plasma-assisted surface modification is diverse and specially designed to cater to the specific requirements of different materials and industrial applications. These systems operate on the principle of generating ionized gas, or plasma, under controlled conditions to interact with the surface of the material being treated. The choice of plasma generation system significantly influences the uniformity, depth, and effectiveness of the surface treatment.

One common type of equipment is the low-pressure plasma chamber, also known as a batch-type system. This system operates under vacuum conditions and is typically used for treating small to medium-sized components in batches. These systems offer precise control over plasma parameters and are highly suitable for complex and delicate parts, such as surgical tools and semiconductor components.

Another widely used system is the atmospheric plasma jet, which is an inline system ideal for treating large surfaces or high-volume production lines. Unlike batch systems, atmospheric plasma jets do not require vacuum environments and can be easily integrated into conveyor-based manufacturing setups. These jets are particularly beneficial for large automotive parts such as dashboards and bumpers where continuous and rapid treatment is necessary.

Dielectric Barrier Discharge (DBD) systems are another category designed for uniform exposure across surfaces, especially for polymers and textiles. These systems function by placing the substrate between two electrodes with a dielectric material in between, allowing for the generation of a uniform plasma discharge across the surface.

Several key parameters must be carefully adjusted and monitored in any plasma treatment process to achieve desired surface modifications. These include the type of gas used, such as oxygen, nitrogen, argon, or hydrogen, which determines the nature of the chemical interaction on the substrate surface. The flow rate of the gas affects the consistency and reactivity of the

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

plasma. Power input and frequency are also crucial, as they determine the energy density and ionization efficiency of the plasma.

Treatment time directly impacts the thickness or depth of the modified layer, while chamber pressure influences plasma density and distribution. Additionally, the substrate material and its distance from the plasma source affect uniformity and effectiveness of the treatment.

Industrial Applications

The practical use of plasma-assisted surface modification is extensive and highly impactful across a range of industries due to its ability to tailor surface properties without altering bulk characteristics.

In the aerospace industry, where performance under extreme conditions is essential, plasma nitriding is widely used to enhance the wear resistance of turbine blades and engine components. Plasma oxidation techniques are employed to develop thermal barrier coatings on space-grade aluminum alloys, offering enhanced resistance to thermal fatigue and environmental degradation.

In the automotive sector, the need for improved surface adhesion and corrosion resistance has made plasma surface treatment an integral part of the manufacturing process. For example, oxygen plasma activation is used on plastic bumpers before painting, ensuring improved paint adhesion and surface finish. Plasma polymer coatings on metal parts enhance corrosion protection, especially for parts exposed to road salts and high humidity.

In the biomedical field, plasma polymerization is used to deposit biocompatible coatings on implants, catheters, and prosthetic devices. These coatings enhance biological interaction and reduce the risk of rejection or infection. Plasma cleaning is also used to sterilize surgical instruments by removing organic contaminants at a microscopic level without the need for chemical disinfectants.

CASE STUDY EXAMPLES

The effectiveness of plasma-assisted surface treatments is best illustrated through real-world case studies in various industrial domains.

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

In the aerospace sector, titanium compressor blades treated with plasma nitriding exhibited twice the operational lifespan compared to untreated components. This was attributed to the increased surface hardness and improved resistance to erosive wear in jet engine environments.

In the automotive industry, polypropylene bumpers subjected to oxygen plasma treatment showed a 40 percent increase in paint adhesion strength. This resulted in better aesthetic quality and reduced paint delamination over time, particularly in regions with fluctuating weather conditions.

In the biomedical domain, surgical-grade stainless steel instruments underwent argon plasma cleaning, resulting in a 95 percent reduction in surface contamination. This level of cleanliness is critical for ensuring sterility in surgical procedures and minimizing the risk of post-operative infections.

Advantages and Limitations

Plasma-assisted surface modification offers numerous advantages that make it a preferred choice over conventional surface treatment methods.

One of the most significant advantages is its environmentally friendly nature. Plasma treatments do not require hazardous chemicals or solvents, thereby reducing the generation of toxic waste and minimizing the environmental footprint. The low thermal budget associated with plasma processes allows for treatment of heat-sensitive materials such as polymers and composites, which would otherwise degrade under high-temperature conditions. Plasma systems also offer uniform treatment over complex geometries, ensuring consistent surface modification on intricate parts and assemblies. Moreover, the flexibility of plasma treatment systems allows for customization of process parameters to suit specific application needs.

Despite these advantages, there are certain limitations associated with plasma technology. High initial equipment cost and the need for periodic maintenance can pose challenges for small and medium enterprises. The effectiveness of plasma treatment is often limited to the surface layer, with only micrometer-scale depth penetration, which may not be sufficient for components subjected to deep mechanical wear. Vacuum-based systems require airtight

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

chambers and are not always compatible with large or awkwardly shaped parts. Additionally, skilled personnel are needed to operate plasma equipment and optimize process parameters for each use case, which may increase operational complexity.

FUTURE SCOPE AND RESEARCH DIRECTIONS

Plasma-assisted technologies continue to evolve, offering exciting possibilities for future research and industrial integration. One promising direction is the development of atmospheric cold plasma systems that operate at room temperature and do not require vacuum conditions. These systems are ideal for treating temperature-sensitive materials and can be integrated inline with existing production lines for real-time processing.

Pulsed plasma systems are another emerging innovation, allowing for precise control over energy delivery and enabling the treatment of delicate materials with minimal thermal impact. Research is also progressing in the area of robotics-assisted plasma processing, where robotic arms integrated with plasma jets can automate the coating and surface activation of complex components in smart manufacturing environments.

In the biomedical sector, bioactive plasma coatings capable of releasing therapeutic agents or promoting cell adhesion are being explored for regenerative medicine and tissue engineering. In the aerospace industry, multifunctional smart coatings that combine wear resistance, thermal stability, and electromagnetic shielding are being investigated to meet the growing demands of next-generation aircraft and space vehicles.

These innovations underscore the potential of plasma-assisted surface engineering to redefine manufacturing and material design paradigms in the coming decades.

CONCLUSION

Plasma-assisted surface modification represents a transformative approach in the field of industrial coatings, offering a unique combination of precision, environmental sustainability, and versatility. Through mechanisms such as plasma nitriding, oxidation, polymerization, and activation, this technology allows for tailored enhancement of surface properties like hardness, corrosion resistance, and adhesion. Its successful application across aerospace, automotive, and biomedical industries attests to its broad utility and effectiveness.

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

Despite certain limitations in cost and depth penetration, the advantages far outweigh the drawbacks, especially in high-performance and safety-critical applications. With ongoing advancements in plasma technology, such as the emergence of cold atmospheric plasmas, pulsed systems, and smart robotic integrations, the scope for future development and adoption continues to expand. As research into multifunctional and bioactive coatings matures, plasma-assisted surface modification is poised to become an indispensable part of modern manufacturing and material science.

REFERENCES

1. Singh, A., & Mehra, R. (2020). Effect of low-temperature plasma nitriding on surface hardness of titanium alloys. *Journal of Materials Science and Engineering*, 45(3), 223–231.
2. Patel, V., & Kumar, S. (2021). Plasma surface treatment of polymers for enhanced adhesion in automotive applications. *Surface Engineering Review*, 38(1), 57–66.
3. Dey, R., & Iyer, P. (2019). Plasma-assisted coating technologies in aerospace components. *International Journal of Aerospace Materials*, 12(2), 85–94.
4. Reddy, N., & Sharma, P. (2022). Plasma polymerization for biocompatible surface coatings: Advances and challenges. *Biomedical Surface Technology*, 19(4), 312–320.
5. Banerjee, S., & Ghosh, A. (2018). Corrosion resistance improvement using plasma oxidation on aluminum substrates. *Corrosion and Surface Protection Journal*, 33(5), 102–109.
6. Kumar, A., & Prasad, B. (2020). Plasma-enhanced surface modification in the biomedical device industry. *Journal of Biomedical Coating Technology*, 27(1), 41–49.
7. Chatterjee, M., & Rao, S. (2021). Comparative evaluation of plasma nitriding and conventional hardening on alloy steels. *Materials Performance Reports*, 14(3), 198–206.
8. Iqbal, Z., & Pandey, T. (2023). Advancements in atmospheric plasma jets for inline industrial applications. *Plasma Science Innovations*, 10(2), 120–129.
9. Sen, H., & Deshmukh, R. (2019). Dielectric barrier discharge plasma and its role in surface energy modification. *Surface Chemistry and Physics*, 28(3), 144–153.
10. Gupta, R., & Malik, D. (2020). Contact angle analysis in plasma-activated polymer surfaces. *Journal of Adhesion Science*, 17(4), 240–248.

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved

11. Sharma, L., & Chauhan, M. (2018). Effect of plasma parameters on corrosion resistance of metal surfaces. *International Surface Engineering Journal*, 22(2), 134–143.
12. Joshi, A., & Patil, Y. (2021). Optimization of plasma surface treatment parameters for high-performance coatings. *Engineering Plasma Journal*, 15(1), 55–63.
13. Dubey, K., & Naik, H. (2019). Plasma modification of industrial ceramics for harsh environments. *Ceramic Engineering Letters*, 16(3), 112–120.
14. Menon, S., & Trivedi, R. (2022). Wear resistance improvement using plasma-treated surfaces in automotive gears. *Automotive Materials Technology Review*, 11(2), 65–74.
15. Verma, D., & Srinivasan, R. (2020). Innovations in plasma-assisted surface modification for medical implants. *Medical Device Materials*, 26(1), 92–99.
16. Pandya, K., & Bhattacharya, L. (2021). Role of gas chemistry in plasma surface modification: A review. *Plasma Physics and Engineering*, 18(2), 200–212.
17. Roy, A., & Sehgal, R. (2019). Integration of plasma systems in smart manufacturing. *Journal of Advanced Production Engineering*, 8(4), 157–165.
18. Mukherjee, N., & Thomas, J. (2023). Real-time diagnostics and control in plasma surface engineering. *Smart Coating Systems*, 9(1), 101–109.
19. Kapoor, S., & Nair, V. (2022). Functionalization of surfaces using plasma polymerization techniques. *Applied Surface Modification Reports*, 20(2), 174–183.
20. Bansal, A., & Narayanan, K. (2023). Future trends in cold atmospheric plasma applications. *Emerging Plasma Technologies*, 7(3), 67–78.

Page 26-36 © MANTECH PUBLICATIONS 2025. All Rights Reserved